



2241 Park Place, Suite B
Minden, NV 89423
(888) 782-8324
www.CHEMEON.com

Technical Data Sheet • CHEMEON® Additive 1378

Description:

Concentrated liquid. Reduces phosphates contamination. Extend bath life and improves seal quality. Effective in both Nickel and Non-Nickel Seals.

Use Directions:

For Phosphate contamination up to 200 mg/l Phosphate add 0.2 % vol. (2 gal CHEMEON Additive 1378 to 1000 gal of seal bath) Additive 1378. Mix the seal bath thoroughly for 1 hour. If phosphates are present then they will begin to precipitate almost immediately. Filtration will be required to remove the floc from the bath. Generally a 5 to 25 micron filter should be used for removal of the precipitated phosphate contamination. The amount of time necessary to remove all of the flock will depend on the size of the filter and the volume of the pump. It will take at least three turnovers of the bath to completely filter the precipitate. The amount of flock depends on the amount of phosphates in the seal bath. The higher the level of the phosphates the more flock which will be produced.

Physical and Safety Data:

CHEMEON Additive 1378 is a clear liquid. CHEMEON Additive 1378 is non-hazardous.

CHEMEON Additive 1378 may be slightly irritating to skin and eyes. In case of contact flush with water for 15 minutes.

Packaging:

55 gallon drum

The information contained in this data sheet is for our customer's general purpose. For specific applications, the user should determine the most suitable conditions for their applications.

The information presented regarding this, or any other product manufactured or supplied by CHEMEON, is offered for your consideration, investigation and verification. Information presented is based on our own data and observations, or other sources believed to be reliable. CHEMEON shall have no liability with respect to any recommendations, instructions, or performance. CHEMEON's sole and exclusive warranty is that its products comply with CHEMEON's published chemical or physical specifications. CHEMEON makes no other warranties, either express or implied with respect to its recommendations, instructions, products, apparatus, process or otherwise, and specifically disclaims any implied warranties or merchantability, suitability, fitness for a particular purpose or otherwise. CHEMEON® Surface Technology LLC