



2241 Park Place, Suite B  
Minden, NV 89423  
(888) 782-8324  
www.CHEMEON.com

## Technical Data Sheet • CHEMEON® Organic Dyes

### Description:

CHEMEON offers a full range of organic dyes for anodized aluminum. This Technical Data Sheet contains information on the following CHEMEON Dyes.

- Fast Gold
- Gold LX
- Gold S
- Gold

### Operating Conditions:

Method of Application:	Immersion
Concentration:	Varies with dye – See color sample
Immersion time:	5 - 15 minutes depending on desired color
Temperature:	120 – 140 °F (50 – 60 °C)
pH:	Varies with dye
Water:	Use low hardness water or deionized water.
Tank:	Stainless steel or other acid resistant material, which is stable to 150 °F

---

Fast Gold  
pH: 5.5-6.0  
Concentration: 0.5 g/L  
Time: 5 min

---

Gold LX  
pH: 7.0-8.0  
Concentration: 1 g/L  
Time: 5 min

### Recommendations for make-up and maintenance:

1. Deionized water or high quality tap water should be used for make-up.
2. The water should be heated to 180 °F on makeup to ensure that the dye dissolves completely, then cooled down to 130 °F.

---

Gold S  
pH: 6.5-7.0  
Concentration: 2 g/L  
Time: 5 min

### Typical anodizing parameters:

Thickness	0.5 mil
Current density	12 amps/ft <sup>2</sup>
Tank temperature	70 °F (21 °C)
Tank chemistry	180 – 200 g/L sulfuric acid 4-12 g/L aluminum ions

---

Gold  
pH: 6.0-7.0  
Concentration: 1 g/L  
Time: 5 min

### Seal parameters: CHEMEON Seal 6100



2241 Park Place, Suite B  
Minden, NV 89423  
(888) 782-8324  
[www.CHEMEON.com](http://www.CHEMEON.com)

Temperature: 160-190°F  
Immersion Time: 10-20 minutes

A mid-temperature nickel seal is recommended to seal the anodic coating and set the dye.

*The information presented regarding this, or any other product manufactured or supplied by CHEMEON, is offered for your consideration, investigation and verification. Information presented is based on our own data and observations, or other sources believed to be reliable. CHEMEON shall have no liability with respect to any recommendations, instructions, or performance. CHEMEON's sole and exclusive warranty is that its products comply with CHEMEON's published chemical or physical specifications. CHEMEON makes no other warranties, either express or implied with respect to its recommendations, instructions, products, apparatus, process or otherwise, and specifically disclaims any implied warranties or merchantability, suitability, fitness for a particular purpose or otherwise. CHEMEON® Surface Technology LLC*